

AN ***1990:617799*** CAPLUS
 DN 113:217799
 TI Cosmetics containing microencapsulated ultraviolet light absorbents
 IN Shimai, Yoshiyuki; Yoshikawa, Itsuji
 PA Pias Co., Ltd., Japan
 SO Jpn. Kokai Tokkyo Koho, 13 pp.
 CODEN: JKXXAF
 DT Patent
 LA Japanese
 IC ICM B01J013-02
 CC 62-4 (Essential Oils and Cosmetics)
 FAN.CNT 1

XP-002151149

	PATENT NO.	KIND	DATE	APPLICATION NO.	DATE
PI	JP 02002867	A2	19900108	JP 1988-150472	19880617
OS	MARPAT 113:217799				
GI	Diagram(s) available in offline prints and/or printed CA Issue.				
AB	Silica particles (0.1-30.0 .mu.m particles) contain benzophenone derivs. (X, Y = C1-24 alkyl, alkoxy, sulfonic acid group, alkali metal salt; m, n = 0-3; k + l = 1-4) as UV light absorbents, forming I-contg. microcapsules. A process for microencapsulation of I using silicic acid alkali metal salts is detailed. Sunscreens contg. the microcapsules are prep'd. and these sunscreens are more compatible with skin than conventional ones. Microcapsules (av. diam. 1.8 .mu.m) contg. 18.22% by wt. 2,2',4,4'-tetrahydroxybenzophenone were prep'd. A sunscreen compn. contg. 30% by wt. of these microcapsules was shown.				
ST	UV absorbent benzophenone silica microcapsule; sunscreen benzophenone silica microcapsule				
IT	Sunburn and Suntan				
	(sunscreens, benzophenones encapsulated in silica microcapsules for)				
IT	119-61-9D, Benzophenone, derivs.. 131-54-4, 2,2'-Dihydroxy-4,4'-dimethoxybenzophenone 131-55-5, 2,2',4,4'-Tetrahydroxybenzophenone 131-56-6, 2,4-Dihydroxybenzophenone				
	RL: BIOL (Biological study)				
	(microcapsules contg., for sunscreens)				
IT	7631-86-9, Silica, biological studies				
	RL: BIOL (Biological study)				
	(microcapsules from, benzophenones-encapsulated, for sunscreens)				

MICROCAPSULE CONTAINING ULTRAVIOLET ABSORBER, PRODUCTION THEREOF AND COSMETIC CONTAINING THE SAME MICROCAPSULE

Patent Number: JP2002867
Publication date: 1990-01-08
Inventor(s): SHIMAI YOSHIYUKI; others: 01
Applicant(s):: PIASUARAIZU KK
Requested Patent: JP2002867
Application Number: JP19880150472 19880617
Priority Number(s):
IPC Classification: B01J13/04 ; A61K7/42 ; B01J13/02
EC Classification:
Equivalents: JP2686484B2

Abstract

PURPOSE: To prevent the absorption of UV in the skin by incorporating a specified benzophenone deriv. into silica-based spherical fine particles of 0.1-30µm average particle size to form microcapsules.

CONSTITUTION: A benzophenone deriv. represented by formula I (where each of X and Y is 1-24C alkyl, alkoxy, sulfonic acid or alkali metal sulfonate, each of m and n is an integer of 0-3 and each of k and l is an integer of 1-4) is dissolved in an aq. soln. of alkali metal silicate. This aq. soln. is mixed with an org. solvent having ≤5% solubility in the benzophenone deriv. and water to prepare a W/O type emulsion and an acidic aq. soln. is mixed with the emulsion. The benzophenone deriv. is then incorporated into silica-based spherical fine particles of 0.1-30µm average particle size to produce microcapsules contg. an UV absorber.

Data supplied from the esp@cenet database - 12

Translation from the Japanese, annexed amendments reincorporated in the body of the patent.

[19] JAPANESE PATENT OFFICE (J.P.) [11] Publication no.: H2 - 2867

[43] Publication date: 08/01/1990

[12] **PUBLISHED, UNEXAMINED JAPANESE
PATENT APPLICATION (A)**

[51] Int. Cl.⁵: B01J 13/04, AS1K 7/42, B01J 13/02

Request for examination not filed

Number of claims: 3

[54] Title of the invention: **Microcapsules enclosing a UV filter, their preparation process and cosmetic containing said microcapsules.**

[21] Application no.: S63-150472

[22] Date of filing: 17/06/1988

[71] Applicants: PIAS CORPORATION

21-3, Toyosaki 3-chôme, Kita-ku, Osaka-shi, Osaka-fu

[72] Inventor(s): Y. SHIMAI

I. YOSHIKAWA

[74] Representative(s): N. FUJIMOTO - patent agent

Subject of the Invention

1. Title of the Invention

Microcapsules enclosing a UV filter, their preparation process and cosmetic containing said microcapsules.

2. Claims

1. Microcapsules enclosing a UV filter characterized in that a benzophenone derivative corresponding to the general formula:

Formula (1)

[in which the m X and n Y designate identical or different alkyl groups of 1 to 24 carbons, alkoxy groups or sulfonic acid groups or their alkali metal salts, m and n are integers between 0 and 3, and k+1 is an integer between 1 and 4] is enclosed in spherical microparticles, of mean diameter of between 0.1 and 30 μ n, made principally of silica.

2. Process of preparation of microcapsules enclosing a UV filter characterized in that a benzophenone derivative corresponding to the general formula:

Formula (1)

[in which the m X and n Y designate identical or different alkyl groups of 1 to 24 carbons, alkoxy groups or sulfonic acid groups or their alkali metal salts, m and n are integers between 0 and 3, and k+1 is an integer between 1 and 4] is enclosed in spherical microparticles, of mean diameter of between 0.1 and 30 μ n, made principally of silica, this by a process that consists in dissolving said benzophenone derivative in an aqueous solution of an alkali metal salt of silicic acid, mixing the aqueous solution obtained with an organic solvent whose solubility in relation to the water and the said benzophenone derivative does not exceed 5% in order to obtain a W/O emulsion, then mixing with said emulsion an acid aqueous solution that can form insoluble precipitates in the water by neutralization of the alkali solutes of said alkali metal salt of silicic acid and benzophenone derivative, then if necessary filtering, water wash and drying.

3. Cosmetic, characterized in that it contains microcapsules obtained by enclosing a benzophenone derivative corresponding to the general formula:

Formula (1)

[in which the m X and n Y designate identical or different alkyl groups of 1 to 24 carbons, alkoxy groups or sulfonic acid groups or their alkali metal salts, m and n are integers between 0 and 3, and k+1 is an integer between 1 and 4] is enclosed in spherical microparticles, of mean diameter of between 0.1 and 30 μ n, made principally of silica.

3. Description of the Invention

[Field of Application]

This invention concerns microcapsules enclosing a UV filter, a process of preparation of such microcapsules, and a cosmetic containing such microcapsules enclosing a UV filter.

[State of the Art]

It is well known that ultraviolet radiation has all types of effects on skin.

UVB radiation (290-320 nm) causes the appearance of skin lesions (erythema, vesicles), followed, after the inflammatory reaction, by browning of the skin.

While UVA radiation (320-400 nm) barely causes erythema, it does share the browning action of UVB radiation.

Ultraviolet radiation also triggers skin pigmentations which take the form of stains and freckles, and favor aging and degeneration of the skin.

In order to remedy this, all kinds of filters were developed in the past that can absorb ultraviolet radiation, in particular in the preparation of cosmetics.

The concern of the cosmeticians was above all to intercept the ultraviolet radiation reaching the skin. Hence the use in cosmetic formulae, with the aim of shielding the skin from ultraviolet radiation, not only of the said UV filters (basically organic such as the derivatives of paraaminobenzoates, benzotriazole, benzophenone, cinnamates, etc.) but also, for instance, of mineral pigments such as titanium dioxide or zinc oxide, which can reflect ultraviolet radiation.

[Problems to be solved]

(a) However, in the prior art, cosmetics incorporating organic UV filters do not always give good sensations on use. Sometimes these filters are also incompatible with the cosmetic bases.

Further, on skin, not only do the UV filters constitute in themselves direct skin irritation factors, but they are sometimes at the origin of transitory irritations through the luminous energy that they absorb.

All UV filter based cosmetics of the prior art face one or other of these problems and are therefore reserved for specific uses.

(b) Cosmetics incorporating mineral pigments certainly avoid the problems of skin or other irritation type, but practice has proved that their screening power is insufficient and they are not able to protect the skin from UV radiation, since it is a well-known fact that UV absorption does not constitute the prime motive for the use of pigments.

With mineral pigments of a grain size in the interception range of visible radiation (sufficiently large diameter), the cosmetic's absorption is particularly mediocre in ultraviolet radiation.

With micronized titanium dioxide, the UV screen effect is greater thanks to the powder's dispersing action on light, but this dispersion is offset by the production of a white film. Further, the cosmetic lacks adhesion and spreadability on the skin, leading at the time of application to the accumulation of thick deposits and a non-transparent esthetic rendering.

In other words, until now there had been practically no success in developing cosmetics that could both screen the skin from UV radiation and satisfy the required conditions as regards in particular skin tolerance, compatibility etc.

This invention sets as a goal solution of the above-mentioned problems, proposing a cosmetic that constitutes a filter and screen sufficiently effective in order

to protect the skin from deleterious UV radiation, that offers excellent performances of skin tolerance, adhesion on skin, spreadability etc., and that gives remarkable sensation on use and impression of transparency.

[Solution proposed]

Following in-depth studies, the applicant discovered that this goal can be attained by encapsulation of a certain type of organic UV filter in a certain type of mineral spherical microparticles and incorporating the microcapsules thus obtained in the cosmetic; the applicant derived this invention from the aforesaid.

This invention in fact proposes, to attain its goal, microcapsules enclosing a UV filter, a process of preparation of such microcapsules, and a cosmetic containing such microcapsules.

The microcapsules according to the invention are characterized in that a benzophenone derivative corresponding to the general formula:

Formula (I)

[in which the m X and n Y designate identical or distinct alkyl groups of 1 to 24 carbons, alkoxy groups or sulfonic acid groups or their alkali metal salts, m and n are integers between 0 and 3, and k+1 is an integer between 1 and 4] is enclosed in spherical microparticles, of mean diameter of between 0.1 and 30 μ n, made principally of silica.

The microcapsule preparation process according to the invention is characterized in that the benzophenone derivative corresponding to the chemical structure described above is enclosed in spherical microparticles, of a mean diameter of between 0.1 and 30 μ m, composed principally of silica, this by a process that consists in dissolving said benzophenone derivative in an aqueous solution of an alkali metal salt of silicic acid, mixing the aqueous solution obtained with an organic solvent whose solubility in relation to the water and the said benzophenone derivative does not exceed 5% in order to obtain a W/O emulsion, then mixing with said emulsion an acid aqueous solution that can form insoluble precipitates in the water by neutralization of the alkali solutes of said alkali metal salt of silicic acid and benzophenone derivative, then if necessary filtering, water wash and drying.

The cosmetic according to the invention is characterized in that it contains the microcapsules described above.

For the benzophenone derivative of the formula cited above, the following compounds for instance can be used:

- (a) 2,2'-dihydroxy-4-methoxybenzophenone
- (b) 2-hydroxy-4-methoxybenzophenone
- (c) 2-hydroxy-4-methoxybenzophenone-5-sulfonic acid
- (d) 2,2'-dihydroxy-4/4'-dimethoxybenzophenone
- (e) 2,2',4,4'-tetrahydroxybenzophenone
- (f) 2,2'-dihydroxy-4/4'-dimethoxybenzophenone-5-sodium sulfonate
- (g) 2,4-dihydroxybenzophenone

- (h) 2-hydroxy-4-methoxybenzophenone-5-sodium sulfonate
- (i) 2-hydroxy-4-octyloxybenzophenone
- (j) 2-hydroxy-4'-methoxybenzophenone
- (k) 2-hydroxybenzophenone
- (l) 4-hydroxybenzophenone
- (m) 2-hydroxy-4-methylbenzophenone
- (n) 2-hydroxy-5-methylbenzophenone
- (o) 2,5-dihydroxybenzophenone
- (p) 2-hydroxy-5-methoxybenzophenone

Obviously this list of examples from (a) to (p) is in no way limited.

For the alkali metal salt of silicic acid of the preparation process according to the invention, it is possible to use for instance sodium silicate JIS no. 1, sodium silicate JIS no. 2, sodium silicate JIS no. 3, sodium metasilicate, potassium silicate ($K_2O \cdot nSiO_2$, n between 2 and 3.8), etc.

For the organic solvent of said preparation process, one might cite inter alia aliphatic saturated hydrocarbons, such as n-hexane, decane, octane, etc., aromatic hydrocarbons such as toluene, benzene, xylene, etc., alicyclic hydrocarbons such as cyclohexane, etc.

Obviously it is possible to use a single one of these organic solvents or to associate several varieties.

For the emulsifier of this preparation process, preferably non-ionic surfactants are used with an HLB of between 3.5 and 6.0. Among the most representative are sorbitan sesquioleate, sorbitan monooleate, polyoxyethylene sorbitan trioleate (POE), etc.

For the acid aqueous solution of said preparation process, use is made preferably of those that contain multivalent anions such as sulfate and phosphate ions, etc. For instance, when the benzophenone derivative is 2,4-dihydroxybenzophenone, 2,2'-dihydroxy-4,4'-dimethoxybenzophenone, or 2,2',4,4'-tetrahydroxybenzophenone, preferably an acid aqueous solution is selected that presents at the end of the reaction a pH not exceeding 5 and better still 3; moreover, the higher its concentration the better.

Obviously, the said alkali metal salt of silicic acid, organic solvent, emulsifier, acid aqueous solution etc., are not limited to the above-mentioned examples.

[Mechanism of the Invention]

(1) Preparation Mechanism



Fig. 1 describes the process of formation of the microparticles making up the microcapsules according to the invention.

Firstly, the benzophenone derivative is dissolved in an aqueous solution of an alkali metal salt of silicic acid; the aqueous solution obtained is then mixed with the organic solvent. A W/O emulsion is obtained, whose discontinuous phase 1 is the liquid mixture of benzophenone derivative and aqueous solution of alkali metal salt of

silicic acid, and whose continuous phase 2 is the organic solvent (Fig. 1-(a)).

This emulsion is then mixed with the acid aqueous solution.

The interface of the discontinuous phase 1 and the acid aqueous solution is then the seat of the following chemical reactions.



(R designates the benzophenone skeleton).

Where R is for instance 2,4-dihydroxybenzophenone, the reaction (b) becomes:

Formula (2)

The process that occurs at the interface is thus a coprecipitation process deriving from the simultaneous occurrence of the two aforesaid chemical reactions.

However, since reaction (a) responds to faster kinetics than reaction (b), a fine film 3 of silica is formed firstly at the interface. Then, the interface reaction pattern progresses over time towards the inside of the internal water-phase to constitute a microcapsule 5 enclosing the product formed 4 (benzophenone derivative) in the silica.

(2) Prevention of elution of the encapsulated benzophenone derivative.

The microcapsules, consisting of a benzophenone derivative enclosed in spherical microparticles made principally of silica, which are obtained by the reaction mechanism described above, also contain a large fixed water fraction. It is therefore recommended to carry out drying at a temperature that is sufficiently high (at least 100°C) but that does not lead to the denaturation of the benzophenone derivative. This drying makes it possible to minimize the elution of the encapsulated benzophenone derivative.

Then, in order to attenuate even more this elution, it is possible to apply if necessary known surface treatments (treatment by silicone oils etc.).

[Examples of implementation]

The invention will be better understood through reading examples of implementation.

Examples of implementation of microcapsules

Implementation example 1

Example of implementation of microcapsules of 2,2',4,4'-tetrahydroxybenzophenone (example of benzophenone derivative according to the invention).

These microcapsules enclose 18.22% in weight of 2,2',4,4'-tetrahydroxybenzophenone of the formula given below in spherical microparticles

made principally of silica, and have a mean grain diameter of 1.8 μm .

Formula (3)

Implementation example 2

Example of implementation of microcapsules of 2,2-dihydroxy-4,4'-dimethoxybenzophenone (example of benzophenone derivative according to the invention).

These microcapsules enclose 22.04% in weight of 2,2'-dihydroxy-4,4'-dimethoxybenzophenone of the formula given below in spherical microparticles made principally of silica, and have a mean grain diameter of 2.2 μm .

Formula (4)

Implementation example 3

Example of implementation of microcapsules of 2,4-dihydroxybenzophenone (example of benzophenone derivative according to the invention).

These microcapsules enclose 19.5% in weight of 2,4-dihydroxybenzophenone of the formula given below in spherical microparticles made principally of silica, and have a mean grain diameter of 3.1 μm .

Formula (5)

The grain diameter of the microcapsules according to the invention is not limited to that of the implementation examples described above. The only condition is that the mean grain diameter of the spherical microparticles making up the outside wall of the microcapsules is between 0.1 and 30 μm .

Reference example

The microcapsules of implementation examples 1 to 3 were subjected to UV absorption spectrum measurement and a sliding friction test.

(1) UV absorption spectrum

The test consisted in adding 20% of the weight of the sample powder (microcapsules of the examples described above) to medicinal Vaseline, proper dispersion by malaxation, then spreading the dispersion between two quartz slides to form a layer 15 μm thick, and measuring its UV absorption spectrum.

We find that the microcapsules of the implementation examples described above have an absorption spectrum corresponding to that of the encapsulated benzophenone derivative, and that gives them a sufficient filtering power in the problematic UVA and UVB ranges (Fig. 3).

(2) Sliding friction

The test consisted of applying a thin film of sample (microcapsules of the examples described above) on a glass slide, placing on it a flat glass slide supporting a weight of 200 g, exercising horizontal traction and measuring the stress required to start the sliding. The results (in relative values) are given in Fig. 4.

We find that the sliding friction is less than with talc, sericite, iron sesquioxide, or titanium oxide, usual ingredients in cosmetics.

This is due certainly to the sphericity of the microcapsules that favor the rolling effect in relation to ingredients such as talc.

Examples of implementation of the microcapsule preparation process

Implementation example 4

Example of carrying out of the preparation process of the 2,2',4,4'-tetrahydroxybenzophenone microcapsules of implementation example 1.

Dissolve 4.05 g of 2,2',4,4'-tetrahydroxybenzophenone in 90 mL of a sodium silicate No. 1 1.5 mol/L solution, then pour this aqueous solution into 130 mL of a 5% toluene solution of a 4/1 mixture of sorbitan sesquioleate and POE sorbitan trioleate, and emulsify for 5 minutes with Homomixer, to prepare a W/O type emulsion.

Pour this emulsion into 450 mL of an aqueous solution mixture of 1.2 mol/L of ammonium sulfate, 0.88 mol/L of sodium dihydrogenophosphate and 0.72 mol/L of phosphoric acid, agitate for one hour and let it rest for 1 night. Then carry out the solid/liquid separation by centrifugation, then, filter, water wash and dry at 120°C.

In this way 19.7 g of microcapsules are obtained, enclosing 18.22% in weight of 2,2',4,4'-tetrahydroxybenzophenone in spherical microparticles made principally of silica, and having a mean grain diameter of 1.8 μm .

Observation of these microcapsules with a scanning electronic microscope confirms that they have a spherical form (Fig. 2).

Implementation example 5

Example of carrying out the preparation process of microcapsules of 2,2'-dihydroxy-4,4'-dimethoxybenzophenone (example of benzophenone derivative according to the invention).

Dissolve 13.5 g of 2,2'-dihydroxy-4,4'-dimethoxybenzophenone in 225 mL of a sodium silicate No. 1 1.5 mol/L solution, then pour this aqueous solution into 400 mL of a 4% benzene solution of a 3/1 mixture of sorbitan sesquioleate and POE sorbitan trioleate, and emulsify for 5 minutes with Homomixer, to prepare a W/O type emulsion.

Pour this emulsion into 1200 mL of an aqueous solution mixture of 1.5 mol/L of ammonium sulfate, 0.75 mol/L of sodium dihydrogenophosphate and 0.75 mol/L of phosphoric acid, agitate for one hour and let it rest for 12 hours. Then apply the same protocol as in implementation example 4.

In this way 50.7 g of microcapsules are obtained, enclosing 22.04% in weight of 2,2'-dihydroxy-4,4'-dimethoxybenzophenone in spherical microparticles made principally of silica, and having a mean grain diameter of 2.2 μm .

Implementation example 6

Example of carrying out the preparation process of microcapsules of 2,4-dihydroxybenzophenone (example of benzophenone derivative according to the

invention).

Dissolve 10.0 g of 2,4-dihydroxybenzophenone in 200 mL of a sodium silicate No. 1 1.5 mol/L solution, then pour this aqueous solution into 350 mL of a 5% n-hexane solution of a 6/1 mixture of sorbitan monooleate and POE sorbitan monooleate, and emulsify for 3 minutes with Homomixer, to prepare a W/O type emulsion.

Pour this emulsion into 1000 mL of an aqueous solution mixture of 1.2 mol/L of sodium dihydrogenophosphate and 1.6 mol/L of phosphoric acid, agitate for one hour and let it rest for 1 night. Then apply the same protocol as in implementation example 4.

In this way 45.2 g of microcapsules are obtained, enclosing 19.52% in weight of 2,4-dihydroxybenzophenone in spherical microparticles made principally of silica, and having a mean grain diameter of 3.1 μm .

Examples of implementation of cosmetics

The microcapsules of the type described above can be incorporated in cosmetics, drugs etc. with the aim of preventing the deleterious effects of UV radiation on the skin.

The dosage of the microcapsules in the cosmetic, while varying according to the nature of the cosmetic, is selected usually, according to the weight of the benzophenone derivative, preferably between 0.1 and 20% in weight, and more preferably between 0.5 and 10% in weight.

The cosmetic according to the invention is prepared with incorporation by the usual methods of the said microcapsules into known cosmetic bases. It can take all cosmetic forms: creams, solutions, sticks, milks, foundation, pomades, etc.

By judicious selection and combination of microcapsules and cosmetic bases, it is in fact possible to prepare all sorts of cosmetics with a UV filtering power, from the basic cosmetic - cosmetic oils made of oil bases, fatty creams and milks made mainly of oil bases, non-fatty creams and milks made mainly of water, water-based toilet waters, etc., - to make-up cosmetics with all their specialties - foundation, fat-based lipsticks etc.

There follows a description of examples of execution of the cosmetic according to the invention.

Implementation example 7

Example of implementation of a powder foundation incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Microcapsules (IE-1)	30.0
(2)	Talc	q.s.f. 100
(3)	Mica	30.0
(4)	Titanium-Mica	1.0

(5)	Titanium oxide	8.0
(6)	Iron sesquioxide	0.7
(7)	Iron oxide yellow	1.8
(8)	Iron oxide black	0.2
(9)	Crystalline cellulose	0.2
(10)	Methylpolysiloxane	4.0
(11)	Liquid paraffin	3.0
(12)	Perhydrosqualene	4.0
(13)	Perfume	q.s.
(14)	Preservative, antioxidant	traces

IE = implementation example

The cosmetic can be prepared as follows: Carefully mix (1)-(9) in the Henschel mixer and add uniformly the mixture of the other ingredients, then mill in breaker and mold by compression.

The cosmetic produces an impression of transparency and displays adhesion. It can be applied in a thin uniform layer on the skin.

It has a very powerful UV screen power.

Unlike mineral pigment-based cosmetics of the prior art, it does not produce a white film.

It gives a velvety sensation on use and good cosmetic performance.

Implementation example 8

Example of implementation of a W/O emulsion foundation incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Microcapsules (IE-2)	10.0
(2)	Microcapsules (IE-3)	10.0
(3)	Titanium dioxide	8.0
(4)	Kaolin	2.0
(5)	Talc	5.0
(6)	Solid paraffin	5.0
(7)	Lanolin	10.0
(8)	Liquid paraffin	27.0
(9)	Sorbitan sesquileate	5.0
(10)	Purified water	q.s.f. 100
(11)	Perfume	q.s.
(12)	Preservative, antioxidant	traces

The cosmetic can be prepared as follows:

Mix (1)-(5) and mill in breaker to obtain a powder. Add to this powder (9) and part of (8), disperse uniformly with the Homomixer, add the other ingredients except for (10) after they have been dissolved by heating and maintain at 70°C (oil phase), bring (10) to 70°C, add to the oil phase, emulsify-disperse uniformly in the Homomixer. Then bring down to 40°C while agitating.

The cosmetic has a very powerful UV screen power. It gives remarkable sensations on use and impression of transparency.

It is remarkably free of the white film and has a good cosmetic performance.

Implementation example 9

Example of implementation of a W/O cream incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Microcrystalline wax	11.0
(2)	Beeswax	4.0
(3)	Vaseline	6.0
(4)	Solid paraffin	5.0
(5)	Perhydrosqualene	30.0
(6)	Adipic acid ester of hexadecyl	10.0
(7)	Glycerol mono-oleic acid ester	3.0
(8)	POE Sorbitan oleate (20)	1.0
(9)	Propylene glycol	2.5
(10)	Microcapsules (IE-1)	10.0
(11)	Purified water	q.s.f. 100
(12)	Perfume	q.s.
(13)	Preservative, antioxidant	traces

The cosmetic can be prepared as follows:

Add (9) and (10) to (11) then bring to and maintain at 80°C (water-phase). Mix and dissolve, heating with the other ingredients, and keep at 80°C (oil phase). After having dispersed uniformly with the Homomixer (10), in the water-phase, add the water-phase to the oil phase and emulsify uniformly in the Homomixer. Then agitate, while cooling.

The cosmetic has an excellent UV screen power. It guarantees better tolerance than prior cosmetics.

It can be applied in thin uniform layer on the skin. It displays adhesion, and remarkable sensations on use and impression of transparency.

It is remarkably free of the white film and gives good cosmetic performance.

Implementation example 10

Example of implementation of an O/W cream incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Beeswax	10.0
(2)	Cetyl alcohol	5.0
(3)	Hydrogenated lanolin	8.0
(4)	Perhydrosqualene	32.5
(5)	Glycerol monostearic acid ester	2.0
(6)	POE Sorbitan monolauric acid ester (20)	2.0
(7)	1,3-Butylene glycol	5.0
(8)	Microcapsules (IE-2)	10.0
(9)	Purified water	q.s.f. 100
(10)	Perfume	q.s.
(11)	Preservative, antioxidant	traces

The cosmetic can be prepared as follows:

Add (7) and (8) to (9) then bring to and maintain at 70°C (water-phase). Mix and dissolve, heating with the other ingredients, and keep at 70°C (oil phase). After having dispersed uniformly with the Homomixer (8), in the water-phase, add the water-phase to the oil phase and emulsify uniformly in the Homomixer. Then agitate, while cooling.

The cosmetic has an excellent UV screen power. It guarantees better tolerance than prior cosmetics.

It can be applied in a thin uniform layer on the skin. It displays adhesion, and remarkable sensations on use and impression of transparency.

It is remarkably free of the white film and gives good cosmetic performance.

Implementation example 11

Example of implementation of a milk incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Stearic acid	2.5
(2)	Cetyl alcohol	1.5
(3)	Vaseline	5.0
(4)	Liquid paraffin	10.0
(5)	POE Sorbitan mono-oleic acid ester (10)	2.0
(6)	Polyethylene glycol 1500	3.0

(7)	Triethanolamine	2,0
(8)	Carboxyvinyl polymer	0.15
(9)	Microcapsules (IE-3)	10.0
(10)	Purified water	q.s.f. 100
(11)	Perfume	q.s.
(12)	Preservative, antioxidant	traces

The cosmetic can be prepared as follows:

Add (6) - (9) to (10), dissolve while heating and maintain at 80°C (water-phase). Mix and dissolve, heating with the other ingredients, and keep at 80°C (oil phase). After having dispersed uniformly with the Homomixer (9), in the water-phase, add the oil phase to the water-phase and emulsify uniformly in the Homomixer. Then bring down to 30°C while agitating.

The cosmetic has an excellent UV screen power. It guarantees better tolerance than prior cosmetics.

It can be applied in a thin uniform layer on the skin. It displays adhesion, and remarkable sensations on use and impression of transparency.

It is remarkably free of the white film and gives good cosmetic performance.

Implementation example 12

Example of implementation of a lip cream incorporating microcapsules according to the invention.

Formula (% in weight)

(1)	Microcapsules (IE-2)	3.0
(2)	Microcapsules (IE-3)	4.0
(3)	Candelilla wax	2.9
(4)	Ceresine	14.9
(5)	[<i>unknown ingredient</i>]	4.8
(6)	Octyldodecanol	7.0
(7)	Diisostearyl malate ¹	35,5
(8)	Glycerol Tri-2-ethylhexanoate	22.2
(9)	Neopentyl glycol dioctanoate	5.6
(10)	Perfume	q.s.
(11)	Preservative, antioxidant	traces

The cosmetic can be prepared as follows:

Add (1) and (2) to part of (7), then process in tricylinder (pigment fraction). Mix and dissolve the other ingredients while heating, add the pigment fraction and disperse

¹ Translator's note: Under reserve. The Japanese term probably has a misprint.

uniformly with the Homomixer. Then pour into a stick mold, cool quickly and enclose in a case.

The cosmetic has an excellent UV screen power. It guarantees better tolerance than prior cosmetics.

It can be applied in thin uniform layer on the lips. It gives remarkable sensations on use and impression of transparency.

It offers a good cosmetic performance.

[Effects of the Invention]

(a) The microcapsules according to the invention, since they enclose the benzophenone derivative (UV filter) in spherical microparticles made of silica and having a mean diameter of between 0.1 and 30 μm , do not place the UV filter in direct contact with the skin. This has the significant effect of diminishing skin irritation and considerably improving tolerance in relation to the UV filters of the prior art.

In consequence the cosmetics containing this type of microcapsules are in themselves less irritating for the skin.

(b) The effect of the powder form of the microcapsules is to facilitate their incorporation, including with the cosmetic bases which do not lend themselves well to incorporation of the UV filters of the prior art.




(c) The spherical form of the microcapsules has the effect of making the cosmetic containing them incomparably easier to spread than the previous mineral pigment based products, and thus of allowing its application in a thin uniform layer, without thick deposits and heaviness on the skin.

(d) Since the spherical microparticles forming the outside film of the microcapsules are made of silica, which possesses a refraction index almost equal to that of the lipid soluble cosmetic bases, the manifestations linked to light diffusion (white film, etc.), which affect the prior titanium oxide based cosmetics, can be avoided.

(e) The cosmetic according to the invention acquires a remarkable impression of transparency and density (filling density) in pressing as well as good cosmetic performance.

(f) The microcapsule preparation process according to the invention, in that it consists of dissolving a benzophenone derivative in an aqueous solution of an alkali metal salt of silicic acid, mixing the aqueous solution obtained with an organic solvent in order to obtain a W/O type emulsion, then mixing with said emulsion an acid aqueous solution that can form insoluble precipitates in the water by neutralization of the alkali solutes of said alkali metal salt of silicic acid and benzophenone derivative, allows preparation of the microcapsules in which the benzophenone derivative is enclosed in spherical microparticles made principally of silica.

In particular, the fact that in the coprecipitation interface process:



(R designates the benzophenone skeleton), reaction (a) progresses more rapidly than reaction (b) guarantees that the benzophenone derivative is in fact trapped inside the spherical microparticles and consequently allows sure preparation of the microcapsules.

4. Brief description of the drawings²

Fig. 1 illustrates the preparation process of the microcapsules.

Fig. 2 presents the UV absorption spectrum of the examples of implementation of the microcapsules.

Fig. 3 presents the results of the sliding friction test of the examples of implementation of the microcapsules.

² Translator's note: An amendment removes fig. 2 (scanning electronic microscope picture of the microcapsules of an implementation example) and rennumbers Figures 3 and 4 as Figures 2 and 3.

Translation of the Illustrations

- [1] (a)
- [2] (b)
- [3] (c)
- [4] Absorbance
- [5] Wavelength (nm)
- [6] A: microcapsules of implementation example 1
B: microcapsules of implementation example 2
C: microcapsules of implementation example 3
D: spherical silica microparticles (mean diameter: 1.8 μm)
E: Talc
- [7] Concentration in solid matter: 20% in weight
Dispersion medium: white petroleum jelly
Sample thickness: 15 μm (sandwich between two quartz slides)
- [8] Talc
- [9] Sericite
- [10] Titanium oxide
- [11] Iron sesquioxide
- [12] Nylon powder
- [13] A: microcapsules of implementation example 1
B: microcapsules of implementation example 2
C: microcapsules of implementation example 3

⑨ 日本国特許庁(JP)

⑩ 特許出願公開

⑪ 公開特許公報(A) 平2-2867

⑫ Int. Cl.

B 01 J 13/04
A 61 K 7/42
B 01 J 13/02

識別記号

庁内整理番号

⑬ 公開 平成2年(1990)1月8日

6971-4C

8317-4G

8317-4G

B 01 J 13/02

A

L

審査請求 未請求 請求項の数 3 (全13頁)

⑭ 発明の名称

紫外線吸収剤内包マイクロカプセル及びその製造方法並びにそのマイクロカプセルを含有する化粧料

⑮ 特 願 昭63-150472

⑯ 出 願 昭63(1988)6月17日

⑰ 発 明 者

島 居

義 信

大阪府高槻市淀の原町50-1

⑰ 発 明 者

吉 川

逸 治

大阪府吹田市江坂町5-17-8 三樹マンション203号

⑱ 出 願 人

ピアス株式会社

大阪府大阪市大淀区豊崎3丁目21番3号

⑲ 代 理 人

弁理士 藤本 昇


明 細 書

1. 発明の名称

紫外線吸収剤内包マイクロカプセル及びその製造方法並びにそのマイクロカプセルを含有する化粧料

2. 特許請求の範囲


1. 一般式



(式中m個のX及びn個のYは各々同一又は異なる炭素数1~24のアルキル基、アルコキシ基又はスルホン酸基若しくはそのアルカリ金属塩を示し、且つm及びnは0~3の整数を示し、k+1は1~4の整数を示す)で表されるベンゾフェノン誘導体を、シリカを主成分とする平均粒径が0.1~30 μ mの球状微粒子

中に内包せしめたことを特徴とする紫外線吸収剤内包マイクロカプセル。


2. 一般式



(式中m個のX及びn個のYは各々同一又は異なる炭素数1~24のアルキル基、アルコキシ基、又はスルホン酸基若しくはそのアルカリ金属塩を示し、且つm及びnは0~3の整数を示し、k+1は1~4の整数を示す)で表されるベンゾフェノン誘導体を、アルカリ金属のケイ酸塩水溶液中に溶解し、その水溶液と、水及び前記ベンゾフェノン誘導体に対する溶解度が5%以下の有機溶媒とを混合してW/O型乳液とし、次に前記アルカリ金属のケイ酸塩及びベンゾフェノン誘導体のアル

カリ塩化物との中和反応により水不溶性沈殿を生成しうる酸性水溶液を前記乳濁液と混合し、その後、必要に応じて濾過、水洗、乾燥することにより、前記ベンゾフェノン誘導体を、シリカを主成分とする平均粒径が0.1~30 μ mの球状微粒子中に内包せしめて製造することを特徴とする紫外線吸収剤内包マイクロカプセルの製造方法。

3. 一般式



(式中m個のX及びn個のYは各々同一又は異なる炭素数1~24のアルキル基、アルコキシ基、又はスルホン酸基若しくはそのアルカリ金属塩を示し、且つm及びnは0~3の整数を示し、k+1は1~4の整数を示す) である。

さらに、紫外線は、皮膚にシミ、ソバカス等の色素沈着を生じさせ、或いは皮膚の老化、変性をもたらす。

そこで、このような種々の問題点を解決するために、従来より種々の紫外線吸収剤が開発されており、たとえば化粧料等にも含有されている。

とりわけ、化粧料の場合には皮膚に対する紫外線遮断の要請が大であり、従って、上記紫外線吸収剤(主として有機系のもの、たとえばパラアミノベンゾエート誘導体、ベンゾトリアゾール誘導体、ベンゾフェノン誘導体、シナノート誘導体等)の他、たとえば紫外線を反射しうる二酸化チタン、酸化亜鉛等の無機顔料を含有させることによって紫外線の経皮吸収を防止する化粧料も市販されている。

(発明が解決しようとする課題)

(イ) しかしながら、上記有機系の紫外線吸収剤を含有した化粧料の場合には、その紫外線吸収剤の化粧料基剤に対する相溶性や使用感が必ずしも良好なものではなかった。

されるベンゾフェノン誘導体を、シリカを主成分とする平均粒径が0.1~30 μ mの球状微粒子中に内包せしめたマイクロカプセルを含有してなることを特徴とする化粧料。

3. 発明の詳細な説明

(産業上の利用分野)

本発明は、紫外線吸収剤を内包したマイクロカプセルと、そのマイクロカプセルの製造方法、並びにその紫外線吸収剤内包マイクロカプセルを含有する化粧料に関するものである。

(従来の技術)

周知のように、紫外線は皮膚に対して種々の影響をもたらすことが知られている。

すなわち、UV-B領域(290~320nm)の紫外線は、皮膚に紅斑や水疱を生ぜしめ、炎症後に皮膚の黒化をもたらす。

又、UV-A領域(320~400nm)の紫外線は、紅斑こそほとんど生じさせないものの、黒化をもたらす点ではUV-Bの紫外線の場合と同様である。

さらに、皮膚に塗布した場合、紫外線吸収剤自体が皮膚に刺激を与える他、このような紫外線吸収剤が光エネルギーを吸収した場合においても皮膚に一過性の刺激を与えるという問題があった。

いずれにしても、従来の紫外線吸収剤を含有する化粧料は、上記のようないずれかの問題点を具有していたために、実際に皮膚に使用するに際しては特定の種類のものに制限されていた。(ロ) 一方、上記無機顔料を含有する化粧料の場合には、皮膚に対する刺激等については問題はないが、本来的に紫外線吸収効果を予定して化粧料に含有されたものではないため、紫外線を十分に遮断できず、紫外線の経皮吸収を防止できないという欠点がある。


特に、可視光線を遮断する領域の粒子径(粒子径が比較的大きいもの)の無機顔料を含有する化粧料は、紫外線での吸収が弱い。

これに対して、微粒子の二酸化チタンを配合した場合、その光散乱効果により、紫外線の遮

すると、上記課題がすべて解決されることを見出し本発明を完成するに至った。

すなわち、本発明は、上記課題解決のために、紫外線吸収剤内包マイクロカプセル、及びそのマイクロカプセルの製造方法、並びにそのマイクロカプセルを含有する化粧料としてなされたもので、マイクロカプセルとしての特徴は、

一般式



式中m個のX及びn個のYは各々同一又は異なる炭素数1~24のアルキル基、アルコキシ基、又はスルホン酸基若しくはそのアルカリ金属塩を示し、且つm及びnは0~3の整数を示す、k+1は1~4の整数を示す)で表されるベンゾフェノン誘導体を、シリカを主成分とする平均粒径が0.

庭効果は得られるが、逆に上記光の散乱によって肌が白っぽく浮いた感じになる。しかも、肌への付着性が悪く、延展性に欠けるため、肌に厚ぼったく付着し、従っていわゆるマークアップの状態が透明感のない仕上がりとなる。

いずれにしても、従来では、紫外線の経皮吸収を防止し、しかも皮膚に対する安全性や相容性等の種々の条件を充足する化粧料はほとんど開発されていなかったのである。

本発明は、上述のような問題点をすべて解決するためになされたもので、皮膚に有害な紫外線の吸収及び透皮効果が良好で皮膚への紫外線の経皮吸収を防止し、しかも、安全性、皮膚への付着力、延展性に優れ、且つ使用感、透明感に優れた化粧料を提供することを課題とするものである。

(課題を解決するための手段)

本発明者等は、このような課題を解決するために鋭意研究を行った結果、ある種の有機系紫外線吸収剤を、ある種の無機系球状微粒子に内包せしめてマイクロカプセル化し、これを化粧料に配合

1~30 μ mの球状微粒子中に内包せしめたことにある。

又、マイクロカプセルの製造方法としての特徴は、上記化学構造を有するベンゾフェノン誘導体を、アルカリ金属のケイ酸塩水溶液中に溶解し、その水溶液と、水及び前記ベンゾフェノン誘導体に対する溶解度が5%以下の有機溶媒とを混合してW/O乳濁液とし、次に前記アルカリ金属のケイ酸塩及びベンゾフェノン誘導体のアルカリ溶解物との中和反応により水不溶性沈澱を生成しうる酸性水溶液を前記乳濁液と混合し、その後、必要に応じて濾過、水洗、乾燥することにより、前記ベンゾフェノン誘導体を、シリカを主成分とする平均粒径が0.1~30 μ mの球状微粒子中に内包せしめて製造することにある。

さらに、化粧料としての特徴は、上記のようなマイクロカプセルを含有せしめたことにある。

尚、上記一般式で表されるベンゾフェノン誘導体としては、たとえば次のものが挙げられる。

(イ) 2, 2'-ジヒドロキシ-4-メトキシベ

ンゾフェノン

(ロ) 2-ヒドロキシ-4-メトキシベンゾフェノン

(ハ) 2-ヒドロキシ-4-メトキシベンゾフェノン-5-スルホン酸

(ニ) 2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノン

(ホ) 2, 2', 4, 4'-テトラヒドロキシベンゾフェノン

(ヘ) 2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノン-5-スルホン酸ナトリウム

(ト) 2, 4-ジヒドロキシベンゾフェノン

(チ) 2-ヒドロキシ-4-メトキシベンゾフェノン-5-スルホン酸 ナトリウム

(リ) 2-ヒドロキシ-4-オクタロキシベンゾフェノン

(ス) 2-ヒドロキシ-4'-メトキシベンゾフェノン

(ル) 2-ヒドロキシベンゾフェノン

- (ヲ) 4-ヒドロキシベンゾフェノン
 (ワ) 2-ヒドロキシ-4-メチルベンゾフェノン
 (カ) 2-ヒドロキシ-5-メチルベンゾフェノン
 (コ) 2,5-ジヒドロキシベンゾフェノン
 (タ) 2-ヒドロキシ-5-メトキシベンゾフェノン

ただし、本発明におけるベンゾフェノン誘導体の種類は上記(イ)～(タ)に限定されるものではない。

さらに、本発明の上記マイクロカプセルの製造方法において、アルカリ金属のケイ酸塩としては、たとえばJ1S1号ケイ酸ナトリウム、J1S2号ケイ酸ナトリウム、J1S3号ケイ酸ナトリウム、メタケイ酸ナトリウム、ケイ酸カリウム($\text{K}_2\text{O} \cdot n\text{SiO}_2$, $n=2\sim3.8$)等が例示される。

又、上記製造方法に用いる有機溶媒としては、 n -ヘキサン、デカン、オクタン等の脂肪族飽和

炭化水素、又はトルエン、ベンゼン、キシレン等の芳香族炭化水素、さらにはシクロヘキサン等の脂環式炭化水素等が挙げられる。

これら各溶媒は、勿論1種単独で、又は2種以上併用して使用することができる。

さらに、該製造方法に用いる乳化剤としては、好ましくはHLB値が3.5～5.0の範囲内にある非イオン界面活性剤の使用ができる。代表的なものとして、たとえばソルビタンセスキオレエート、ソルビタンモノオレエート、ポリオキシエチレンソルビタントリオレエート等がある。

さらに、該製造方法に用いる酸性水溶液としては、硫酸イオンやリン酸イオン等、多価陰イオンを含有するものが好ましい。たとえば上記ベンゾフェノン誘導体が2,4-ジヒドロキシベンゾフェノン、2,2'-ジヒドロキシ-4,4'-ジメトキシベンゾフェノン、2,2',4,4'-テトラヒドロキシベンゾフェノンの等の場合には、反応終了後のpHが5以下、とりわけ3以下である酸性水溶液が好ましく、又、その濃度は高い程

好ましい。

ただし、上記アルカリ金属のケイ酸塩、有機溶媒、乳化剤、酸性水溶液等の種類は上記のものに限定されない。

(作用)




(1) 調製過程に關して

第1図は本発明のマイクロカプセルの微粒生成過程を示す説明図である。

先ず、ベンゾフェノン誘導体をアルカリ金属のケイ酸塩水溶液中に溶解し、その水溶液と有機溶媒とを混合すると、第1図(イ)に示すように、上記ベンゾフェノン誘導体とアルカリ金属のケイ酸塩水溶液との混合液を分散質1とし、有機溶媒を分散質2とするW/O型乳剤が調製される。


次に、この乳剤を上記酸性水溶液と混合する。

このとき、上記分散質1と酸性水溶液との界面において次の化学反応が生ずる。



(ここでRはベンゾフェノン骨格を示す)

尚、この(b)の反応において、Rがたとえば2,4-ジヒドロキシベンゾフェノンの場合は、



本発明における界面の化学反応は、上記の反応式のように反応し、この2つの化学反応が同時進行する共沈反応である。

しかしながら、反応速度の面で(a)の反応が


以下、本発明の実施例について説明する。

〔マイクロカプセルの実施例〕

実施例1


本実施例は、本発明におけるベンゾフェノン誘導体の一例である2, 2', 4, 4'-テトラヒドロキシベンゾフェノンを内包するマイクロカプセルについての実施例である。

すなわち、本実施例におけるマイクロカプセルは、シリカを主成分とする球状微粒子中に、下記式の2, 2', 4, 4'-テトラヒドロキシベンゾフェノンを18.22重量%内包して構成されたもので、その平均粒子径は1.8 μ mである。



実施例2

本実施例は、本発明におけるベンゾフェノン誘



すなわち、本実施例におけるマイクロカプセルは、シリカを主成分とする球状微粒子中に、上記式の2, 4-ジヒドロキシベンゾフェノンを19.5重量%内包して構成されたもので、その平均粒子径は3.1 μ mである。

尚、本発明のマイクロカプセルの粒子径は上記各実施例に限定されるものではなく、要は、そのマイクロカプセルの外壁を構成する球状微粒子の平均粒子径が0.1~30 μ mに形成されていればよい。

参考例

上記実施例1~3のマイクロカプセルについて紫外線吸収スペクトルを測定し、且つすべり摩擦についての試験を行った。

(1) 紫外線吸収スペクトル

局方の白色ワセリン中に上記各実施例の試料

(b) の反応より速く進行するため、先ず、上記界面においてシリカの薄膜3が形成され、その後時間の経過とともに、界面反応が内水相の内側に進行し、ベンゾフェノン誘導体の生成物4がシリカに内包された状態でマイクロカプセル5が製造されることとなるのである。

(2) 内包されたベンゾフェノン誘導体の溶出防止


上記反応機構で得られたシリカを主成分とする球状微粒子中にベンゾフェノン誘導体を内包せしめたマイクロカプセルには、多量の付着水分が含まれているため、ベンゾフェノン誘導体が腐食しない程度に100℃以上の高温で乾燥することが好ましい。この操作によって、内包されたベンゾフェノン誘導体の溶出が極力抑制されることとなるのである。

又、その後、必要に応じてシリコンオイル処理等の公知の表面処理を行うことも可能であり、内包されたベンゾフェノン誘導体の溶出が抑制される。

(実施例)

導体の一例である2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノンを内包するマイクロカプセルについての実施例である。

すなわち、本実施例におけるマイクロカプセルは、シリカを主成分とする球状微粒子中に、下記式の2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノンを22.04重量%内包して構成されたもので、その平均粒子径は2.2 μ mである。



実施例3

本実施例は、本発明におけるベンゾフェノン誘導体の一例である2, 4-ジヒドロキシベンゾフェノンを内包するマイクロカプセルについての実施例である。

折光率を20℃で測定し、十分攪り込んで分散させ、石英板の間に塗布し、厚み15 μ mとしてその紫外線吸収スペクトルを測定した。

その結果、第3図に示すように、上記各実施例のマイクロカプセルは、内包するベンゾフェノン誘導体の紫外線吸収スペクトルに相当する吸収スペクトルを示し、表皮吸収との関係で問題となるUV-A若しくはUV-B領域の紫外線に対して十分な紫外線吸収能を示している。

(2) すべり摩擦

上記各実施例の試料をガラス板の上に薄く塗布し、さらにその上に200 gの分銅をのせた平らなガラス板に置き、水平に引いたとき、滑っている時点での力の大きさを測定し、その相対値を第4図のように棒グラフで示した。

その結果、一般の化粧品に含有されているタルク、セリサイト、ベンガラ、酸化チタンと比べてすべり摩擦が小さいことが判明した。

これは、マイクロカプセルが真球状を呈しているため、上記タルク等と比べ、ローリング効果

を示す。

これによって、シリカを主成分とする球状微粒子中に2, 2', 4, 4'-テトラヒドロキシベンゾフェノンを18.22重量%内包する平均粒子径1.8 μ mのマイクロカプセル19.7gを得た。

尚、本実施例のマイクロカプセルを、走査電子顕微鏡で観察したところ、第2図のように真球状を呈していることを確認した。

実施例5

本実施例は、本発明におけるベンゾフェノン誘導体の一例である2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノンを内包するマイクロカプセルを製造する方法についての実施例である。

先ず、2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノン13.5gを、1.5mol/lの1号ケイ酸ナトリウム溶液225 mlに溶解し、この水溶液をソルビタンセスキオレエートとポリオキシエチレンソルビタントリオレエートとの混合物(混合比3:1)の4%ベンゼン溶液400mlに注

入し、5分間ホモミキサーで乳化し、W/O型乳剤を調製する。

実施例6

本実施例は、上記実施例1の2, 2', 4, 4'-テトラヒドロキシベンゾフェノンを内包するマイクロカプセルを製造する方法についての実施例である。

先ず、2, 2', 4, 4'-テトラヒドロキシベンゾフェノン4.05gを、1.5mol/lの1号ケイ酸ナトリウム溶液90mlに溶解し、この水溶液をソルビタンセスキオレエートとポリオキシエチレンソルビタントリオレエートとの混合物(混合比4:1)の5%トルエン溶液150mlに注ぎ、5分間ホモミキサーで乳化し、W/O型乳剤を調製する。

次に、この乳剤を1.2 mol/l 硫酸アンモニウム、0.88mol/l リン酸2水素ナトリウム及び0.72 mol/l リン酸との混合水溶液450 ml中に注入し、1時間攪拌し1晩静置する。その後、遠心分離により固液分離した後、濾過、水洗し、120℃で乾

燥し、5分間ホモミキサーで乳化し、W/O型乳剤を調製する。

次に、この乳剤を1.5 mol/l 硫酸アンモニウム、0.75mol/l リン酸2水素ナトリウム及び0.75 mol/l リン酸との混合水溶液1200ml中に注入し、1時間攪拌し12時間静置する。その後、上記実施例4と同様の操作を行い、シリカを主成分とする球状微粒子中に2, 2'-ジヒドロキシ-4, 4'-ジメトキシベンゾフェノンを22.04重量%内包する平均粒子径2.2 μ mのマイクロカプセル50.7gを得た。

実施例8

本実施例は、本発明におけるベンゾフェノン誘導体の一例である2, 4-ジヒドロキシベンゾフェノンを内包するマイクロカプセルを製造する方法についての実施例である。

先ず、2, 4-ジヒドロキシベンゾフェノン10.0gを、1.5mol/lの1号ケイ酸ナトリウム溶液200 mlに溶解し、この水溶液をソルビタンセスキオレエートとポリオキシエチレンソルビタンモノオ

レーンとの混合物（混合比5:1）の5% n-ヘキサン溶液350mlに注ぎ、3分間ホモミキサーで乳化し、W/O型乳液を調製する。

次に、この乳液を1.2 mol/lリン酸2水素ナトリウムと1.8 mol/lリン酸との混合水溶液3000ml中に注入し、1時間攪拌し1晩静置する。その後、上記実施例4と同様の操作を行い、シリカを主成分とする球状微粒子中に2,4-ジヒドロキシベンゾフェノンをもれ、52重量%内包する平均粒子径3.1μmのマイクロカプセル45.2gを得た。

〔化粧料の実施例〕

上記のようなマイクロカプセルは、皮膚に対する紫外線の遮断を防止する目的で化粧料、医薬品等に配合することができる。

本発明のマイクロカプセルの化粧料への配合料は、化粧料の種類によっても異なるが、一般にはベンゾフェノン誘導体として0.1~20重量%、とりわけ0.5~10重量%になるようにするのが好ましい。

本発明の化粧料は、上記のようなマイクロカプ

セルを常法により公知の化粧料基剤に配合し、クリーム、粉粧、スティック、乳液、ファンデーション、軟膏等の種々の剤型にすることにより調製される。

すなわち、上記のようなマイクロカプセルを化粧料基剤に配合して選択使用することにより、オイル基剤の化粧油、多量にオイル基剤を配合する油状クリーム、油性乳液、水が多量に配合する乳液状クリームや水性乳液、水ベースの化粧水等の基礎化粧品から油剤を基剤とするファンデーションやリップスティック等の各種メーキャップ化粧料に至るまで、紫外線吸収効果を有するあらゆる形態の化粧料を製造することが可能となる。

次に、本発明の化粧料の実施例について説明する。

実施例7

本実施例は、本発明のマイクロカプセルをいわゆるパウダーファンデーションに配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとお

りである。

成分	重量%
① 実施例1のマイクロカプセル	30.0
② タルク	数量
③ マイカ	30.0
④ 無水チタン	1.0
⑤ 酸化チタン	8.0
⑥ ベンガラ	0.7
⑦ 黄酸化鉄	1.8
⑧ 黒酸化鉄	0.2
⑨ 結晶セルロース	0.2
⑩ メチルポリシロキサン	4.0
⑪ 硬脂パラフィン	3.0
⑫ ステアラン	4.0
⑬ 香料	適量
⑭ 防腐剤、酸化防止剤	適量

本実施例の化粧料を製造する場合には、上記①~⑭をベンツェルミキサーでよくかき混ぜながらこれにその他の成分を混合したものを均一に加え、粉砕機で処理し、圧縮成形することによって製造

される。

本実施例の化粧料は、透明感、密着性があり、肌によく均一に付着することが可能であった。

又、紫外線遮断効果が極めて大であることが認められた。

しかも、従来の無機顔料を配合した化粧料のように、白っぽさが際立って出ることもない。

さらに、ソフトな使用感が得られるとともに、化粧持続性も良好であった。

実施例8

本実施例は、本発明のマイクロカプセルをW/O型乳化型ファンデーションに配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとおりである。

成分	重量%
① 実施例2のマイクロカプセル	10.0
② 実施例3のマイクロカプセル	10.0
③ 二酸化チタン	0.0
④ カオリン	2.0

⑤	タルク	5.0
⑥	固形パラフィン	5.0
⑦	ラノリン	10.0
⑧	流動パラフィン	27.0
⑨	ソルビタンセスキオレエート	5.0
⑩	精製水	残量
⑪	香料	適量
⑫	防腐剤、酸化防止剤	適量

本実施例の化粧料を製造するには、先ず、①～⑤を混合し、研砕機で処理して粉末を得る。次にこの粉末に上記⑥の一部と⑧を加え、ホモミキサーで均一に分散させ、⑩を除く他の成分を加熱溶解してこれに加え、70℃に保つ（油相）。その後、⑨を70℃に加熱し、油相に加えホモミキサーで均一に乳化分散させ、乳化後に掻き混ぜながら40℃まで冷却する。

本実施例の化粧料は、紫外線遮断効果が大きく、使用感、透明感が優れている。

又、白さの浮き防止効果も優れており、化粧持続性も良好であった。

⑫ 防腐剤、酸化防止剤 適量

本実施例の化粧料を製造するには、先ず、①に⑦及び⑧を加え、加熱して80℃に保つ（水相）。又、他の成分を混合し、加熱溶解して80℃に保つ（油相）。ホモミキサーで水相中の⑦を均一に分散させた後、油相に水相を加え、ホモミキサーで均一に乳化し、その乳化後に冷却しながら掻き混ぜることによって上記化粧料が製造される。

本実施例の化粧料は、紫外線遮断効果に優れ、従来の化粧料と比べて安全性が高い。

又、肌に均一に密着し、密着性があり、しかも使用感、透明感が優れている。

又、白さの浮き防止効果も優れており、化粧持続性も良好であった。

実施例10

本実施例は、本発明のマイクロカプセルをO/W型クリームに配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとおりである。

実施例9

本実施例は、本発明のマイクロカプセルをW/O型クリームに配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとおりである。

成分	重量%
① ミタロクリスタリンワックス	11.0
② ミツロウ	4.0
③ ワセリン	6.0
④ 固形パラフィン	5.0
⑤ スクワラン	30.0
⑥ ヘキサデシルアジピン酸エステル	10.0
⑦ グリセリンモノオレイン酸エステル	3.0
⑧ ポリオキシエチレン (20)	
ソルビタンオレエート	1.0
⑨ プロピレングリコール	2.5
⑩ 実施例1のマイクロカプセル	10.0
⑪ 精製水	残量
⑫ 香料	適量

成分	重量%
① ミツロウ	10.0
② セチルアルコール	5.0
③ 水添ラノリン	8.0
④ スクワラン	32.5
⑤ グリセリンモノステアリン酸エステル	2.0
⑥ ポリオキシエチレン (20) ソルビタンモノラウリン酸エステル	2.0
⑦ 1,3-ブチレングリコール	5.0
⑧ 実施例2のマイクロカプセル	10.0
⑨ 精製水	残量
⑩ 香料	適量
⑪ 防腐剤、酸化防止剤	適量

本実施例の化粧料を製造するには、先ず、②に⑦及び⑧を加え、加熱して70℃に保つ（水相）。又、他の成分を混合し、加熱溶解して70℃に保つ（油相）。ホモミキサーで水相中の⑦を均一に分散させた後、水相に油相を加え、ホモミキサーで均一に乳化し、その乳化後に冷却しながら掻き混ぜることによって上記化粧料が製造される。

本実施例の化粧料は、紫外線透過効果に優れ、従来の化粧料と比べて安全性が高い。

又、肌均一に薄く付き、密着性があり、しかも使用感、透明感が優れている。

又、白さの浮き防止効果も優れており、化粧持続性も良好であった。

実施例 1.1

本実施例は、本発明のマイクロカプセルを乳液に配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとおりである。

成分	重量%
① ステアリン酸	2.5
② セチルアルコール	1.5
③ ワセリン	5.0
④ 顔料パラフィン	10.0
⑤ ポリオキシエチレン (10) モノオレイン酸エステル	2.0
⑥ ポリエチレングリコール1500	3.0
⑦ トリエタノールアミン	2.0

本実施例は、本発明のマイクロカプセルをリップクリームに配合した化粧料についての実施例である。

すなわち、本実施例の化粧料の組成は次のとおりである。

成分	重量%
① 実施例2のマイクロカプセル	3.0
② 実施例3のマイクロカプセル	4.0
③ キャンデリラロウ	2.9
④ ヒレシン	14.0
⑤ レジナー	4.8
⑥ オクタルドデカノール	7.0
⑦ ジイソステアリルアレート	35.5
⑧ トリー-2-エチルヘキサン酸グリセリン	22.2
⑨ ジオクタン酸ネオペンチルグリコール	5.6
⑩ 香料	適量
⑪ 防腐剤、酸化防止剤	微量

本実施例の化粧料を製造するには、先ず、①、

⑧ カルボキシビニルポリマー	0.15
⑨ 実施例3のマイクロカプセル	10.0
⑩ 精製水	適量
⑪ 香料	適量
⑫ 防腐剤、酸化防止剤	微量

本実施例の化粧料を製造するには、先ず、⑩に⑧乃至⑨を加え、加熱溶解して80℃に保つ（水相）。又、他の成分を混合し、加熱溶解して60℃に保つ（油相）。ホモミキサーで水相中の⑧を均一分散させた後、水相に油相を加え、ホモミキサーで均一に乳化し、その乳化後に極き混ぜながら30℃まで冷却することによって上記化粧料が製造される。

本実施例の化粧料は、紫外線透過効果に優れ、従来の化粧料と比べて安全性が高い。

又、肌均一に薄く付き、密着性があり、しかも使用感、透明感が優れている。

又、白さの浮き防止効果も優れており、化粧持続性も良好であった。

実施例 1.2

②を①の一部に加え、3本ローラで処理し、顔料部とする。次に、他の成分を混合し、加熱溶解した後、上記顔料部を加え、ホモミキサーで均一分散させる。そして、分散後に型に流し込んで急冷し、スティック状になったものを容器に差し込み、フレーミングを行う。このようにして上記化粧料が製造されることとなる。

本実施例の化粧料は、紫外線透過効果に優れ、従来の化粧料と比べて安全性が高い。

又、唇に薄く均一に付き、しかも使用感、透明感が優れている。

さらに、化粧持続性も良好であった。

(発明の効果)

(イ) 以上のように、本発明のマイクロカプセルは、紫外線吸収剤であるベンゾフェノン誘導体を、シリカを成分とする平均粒径が0.1~30μmの球状微粒子中に内包せしめて構成したものであるため、紫外線吸収剤が直接皮膚に接触することがなく、従って皮膚への刺激が軽減されることとなり、その安全性が従来の紫外線吸収剤に

比べて大粒に高められることになるという顕著な効果がある。

よって、このようなマイクロカプセルを含有した化粧料においても、皮膚に対する刺激緩和効果が得られるという利点がある。

(ロ) 又、マイクロカプセル自体が粉体であるので、従来の紫外線吸収剤の配合が困難であった化粧料基剤に対しても容易に配合することが可能になるという効果がある。

(ハ) さらに、マイクロカプセルが真球状の粉体であるため、このようなマイクロカプセルを含有した化粧料の延展性は、無機顔料を含有した従来の化粧料に比べて非常に良好であり、肌に対して厚ぼったく付着することなく薄く均一に付着し、肌に負担をかけることがないという効果がある。


(ニ) しかも、このような化粧料においては、含有されているマイクロカプセルの外壁を構成する球状微粒子が、化粧料基剤中の油溶剤と光の屈折率が略等しいシリカで構成されているため、

従来の酸化チタンを含有する化粧料のように光の散乱に基つき肌が白く浮き出たような印象を与えることがないという利点がある。


(ホ) 又、上記のような化粧料は透明感に優れ、プレス充填性に優れ、化粧持続性が良好であるという利点がある。

(ヘ) さらに、本発明の製造方法においては、ベンゾフェノン誘導体を、アルカリ金属のケイ酸塩水溶液中に溶解し、その水溶液と有機溶媒とを混合してW/O型乳濁液とし、次に前記アルカリ金属のケイ酸塩及びベンゾフェノン誘導体のアルカリ溶解物との中和反応により水不溶性沈澱を生成しうる酸性水溶液を前記乳濁液と混合してマイクロカプセルを製造する方法なるため、前記ベンゾフェノン誘導体は、シリカを主成分とする球状微粒子中に内包されてマイクロカプセルが製造できることとなる。

特に、界面における次の共沈反応



及び



(ここでRはベンゾフェノン骨格を示す)において、上記(a)の反応が(b)の反応より速く進行するため、ベンゾフェノン誘導体が球状微粒子中に確実には包まれ、従ってマイクロカプセルの製造が確実に行えるという効果がある。

4. 図面の簡単な説明

第1図はマイクロカプセルの製造過程を示す説明図。


第2図は一実施例のマイクロカプセルの走査電子顕微鏡による拡大写真。

第3図は一実施例のマイクロカプセルの紫外線吸収スペクトルのチャート図。


第4図は一実施例のマイクロカプセルのすべり摩擦試験のグラフを示す。

出願人 ビアス株式会社

代理人 弁理士 藤本昇




第2図



10000x


第 3 図



A: 実施例 1 のマイクロカプセル
B: 実施例 2 のマイクロカプセル
C: 実施例 3 のマイクロカプセル
D: シリカ球状微粒子 (平均粒径 1.8 μm)
E: タルク

固体濃度: 20wt% 分散媒: 白色ワセリン
試料厚さ: 15 μm (石英板の間にサンドウィッチ)

第 4 図



A: 実施例 1 のマイクロカプセル
B: 実施例 2 のマイクロカプセル
C: 実施例 3 のマイクロカプセル

手続補正書 (方式)

昭和 63 年 10 月 26 日

特許庁長官 西 岡 文 雄 閣下

1. 事件の表示

昭和 63 年特許願第 150472 号

2. 発明の名称

紫外線吸収剤内包マイクロカプセル及びその製造方法並びにそのマイクロカプセルを含む化粧料

3. 補正をする者

事件との関係 特許出願人

住 所

名 称 ビアス株式会社

4. 代理人

住 所 542 大阪市南区南船場 2 丁目 6 番 8 号

長堀コミュニティビル

電話 (06) 271-7008

氏 名 (7433) 弁護士 西本 昇

5. 補正命令の日付

昭和 63 年 9 月 27 日

6. 補正の対象

明細書の図面の簡単な説明の項及び図面。

7. 補正の内容

別紙の通り。

8. 補正の内容

- (1) 明細書第 37 頁第 11 行目～第 12 行目の「第 2 図は……大分度。」を削除。
- (2) 明細書第 37 頁第 13 行目の「第 3 図」を「第 2 図」に補正。
- (3) 明細書第 37 頁第 15 行目の「第 4 図」を「第 3 図」に補正。
- (4) 図面第 1 図～第 3 図を別紙のとおり補正。
- (5) 図面第 4 図を削除。

図 1




図 3





図 2



A: 実施例 1 のマイクロカプセル
B: 実施例 2 のマイクロカプセル
C: 実施例 3 のマイクロカプセル
D: フェルロ酸鉄粒子 (平均粒径 1.5 μm)
E: フェルロ

固相濃度: 20 wt% 分散媒: 白色ワセリン
分散媒: 15 μm (分散媒の粒径は 1.5 μm)

特許庁長官 敬 啓

平成 1年 9月 16日

特許庁長官 敬 啓

1. 事件の表示

特許第63年特許第15072号

2. 発明の名称

発明は、特許第63年特許第15072号の発明に係る、
製造方法及びそのマイクロカプセルを含む
硬化材料

3. 補正をする者

事件との関係 特許出願人

住 所

名 称

ビナス株式会社

4. 代理人

住 所 542 大阪市中央区南船場2丁目6番1号

氏 名 佐々木 隆雄

電話 (06)271-7908

氏 名 (7133) 佐々木 隆雄

5. 補正命令の日付

日 付

6. 補正により増加する発明の数

7. 補正の対象

明細書の発明の記載事項の補正。

8. 補正の方式

別紙の通り。

方式 特許



8. 補正の内容

- (1) 明細書第5頁第14行目及び第6頁第14行目の「反応吸収」を「反応照射」に補正。
- (2) 明細書第7頁第6行目〜第7行目の「反応吸収」を「反応照射」に補正。
- (3) 明細書第7頁第12行目〜第13行目の「反応吸収」を「反応照射」に補正。
- (4) 明細書第13頁第7行目の「反応吸収」を「反応照射」に補正。
- (5) 明細書第23頁第15行目の「配合料」を「配合剤」に補正。

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.